

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 54-161509

(43)Date of publication of application : 21.12.1979

(51)Int.Cl.

G22C 29/00

B23K 35/00

(21)Application number : 53-069894

(71)Applicant : TOSHIBA CORP

(22)Date of filing : 12.06.1978

(72)Inventor : TAKAYANAGI EIICHI

(54) SOLDERING TOOL

(57)Abstract:

PURPOSE: To manufacture a soldering tool with superior hardness, corrosion resistance, wear resistance and long life by mixing one or more out of W, Mo and Cr carbides with highly electrically conductive metal such as Ag or Cu and one or more out of Co, Ni and Fe in the form of powder followed by compacting and calcination.

CONSTITUTION: 20W50% of powder of at least one kind of metal carbide of high hardness such as tungsten carbide, molybdenum carbide or chromium carbide is mixed with 40W80% of powder of highly electrically conductive metal such as silver or copper and 0.1W10% of powder of at least one of Co, Ni and Fe as a binder for the metal carbide and conductive metal. This mixt. is compacted into a soldering iron and sintered to obtain a soldering tool with good wettability to solder, superior corrosion resistance to solder, high hardness and long life.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

JP54161509

Publication Title:

SOLDERING TOOL

Abstract:

PURPOSE:To manufacture a soldering tool with superior hardness, corrosion resistance, wear resistance and long life by mixing one or more out of W, Mo and Cr carbides with highly electrically conductive metal such as Ag or Cu and one or more out of Co, Ni and Fe in the form of powder followed by compacting and calcination.

CONSTITUTION:20-50% of powder of at least one kind of metal carbide of high hardness such as tungsten carbide, molybdenum carbide or chromium carbide is mixed with 40-80% of powder of highly electrically conductive metal such as silver or copper and 0.1-10% of powder of at least one of Co, Ni and Fe as a binder for the metal carbide and conductive metal. This mixt. is compacted into a soldering iron and sintered to obtain a soldering tool with good wettability to solder, superior corrosion resistance to solder, high hardness and long life.

Data supplied from the esp@cenet database - <http://ep.espacenet.com>

This Patent PDF Generated by Patent Fetcher(TM), a service of Patent Logistics, LLC

⑨日本国特許庁(JP)

⑩特許出願公開

⑪公開特許公報(A)

昭54--161509

⑫Int. Cl.²
C 22 C 29/00
B 23 K 35/00

識別記号
1 0 2

⑬日本分類
10 G 52
10 A 61
12 B 106

庁内整理番号
6411-4K
7362-4E

⑭公開 昭和54年(1979)12月21日

発明の数 1
審査請求 未請求

(全 3 頁)

⑮半田接合具

芝浦電気株式会社横浜金属工場
内

⑯特 願 昭53--69894

⑰出 願 人 東京芝浦電気株式会社

⑱出 願 昭53(1978)6月12日

川崎市幸区堀川町72番地

⑲発 明 者 高柳栄一

⑳代 理 人 弁理士 井上一男

横浜市磯子区新杉田町8 東京

明 細 書

1. 発明の名称 半 田 接 合 具

2. 特許請求の範囲

少なくともろう材に接触する部分が次の組成の材料にて形成されたことを特徴とする半田接合具。

炭化タングステン、炭化モリブデン、炭化クロムの少なくとも1種と、銀またはおよび銅と、コバルト、ニッケル、鉄の少なくとも1種とから成る複合脆断合金。

3. 発明の詳細な説明

この発明は半田接合具の改良に関し、とくに硬さと耐食性を向上させて長寿命とすることを目的としたものである。

半田ごては普通断面に示すような形状をしており、半田づけ作業に用いられているが、この半田ごてに要求される特性は次のようなものである。すなわち(1)軟ろう材とのぬれ性が良好なこと、(2)軟ろう材の中に含まれている烙けた Sn や Pb に侵されないこと、(3)熱伝導性がよいこと、(4)熱容量が大さいこと、(5)十分な機械的強度を有すること

などである。

従来これらの特性からみて半田ごての材料としては電気銅が多く用いられていて、また銅-タングステンあるいは銀-タングステンなどの合金も用いられている。しかしながらこれらの材料を用いたものには次のような欠点があつた。すなわち銅を用いた半田ごては軟かくて長期の使用に耐えず、ある種の軟ろう材には侵食されることがあつて、半田ごてとしての寿命が短いものである。また銅-タングステンなどを用いた半田ごては削鋭剛からなるものの欠点である硬さや耐摩耗性を改善したものであるが、半田ごてとして要請される特性を得ることはいまだ改善が十分でない。

この発明はこのような欠点からなされたものであつて、従来の欠点を除去して長寿命化のはかられた半田ごてを提供するものである。すなわち、少なくともろう材と接触する半田接合具の部分に用いる材料として炭化タングステン、炭化モリブデン、炭化クロムの少なくとも1種と、銀またはおよび銅と、コバルト、ニッケル、鉄の少なくとも

特開昭54-161509(2)

1層とから成る複合焼結合金を用い、硬さと耐食性、耐摩耗性とを著しく向上させた半田ごてを形成する

このようにして半田ごてを形成すると、金属炭化物を含有することで半田ごてとしての特性の改善がなされるうえに、さらにコバルト、ニッケル、鉄の内少なくとも1種が加えられたため、これらが前記金属炭化物の粒子を周囲にかたむく役目をはたすことになって、これらの材料からなる半田ごての硬さ、耐食性等の特性を著しく向上させることになる。

図面に示す半田ごて(1)の先端に位置し、ろう材と接触するチップ部分(2)の特性について、従来の材料から成るものも併記して次の表に示す。

(以下空白)

チップ材料	硬さ (HRA)	耐食性	耐摩耗性	耐熱性
1 58Cu-WC-4Co	58	108	85	820
2 58Cu-WC-4Fe	58	108	85	810
3 60Cu-WC-2Ni	55	100	84	810
4 58Ag-WC-4Co	55	108	88	808
5 58Cu-20WC-20MoC-2Fe	61	115	81	805
6 60Cu-W	57	70	85	160
7 Cu	100	60	100	100

この表の1, 2, 3, 4および5はこの発明のもので、6と7は比較例である。硬さは銅(Cu)の値を100として、それぞれ比較値で示し、硬さの単位はロックウェルBスケールにて示す。耐食性の評価は50×50×0.5mmの試料を8h-50Pb半田の浴槽に2時間浸した後に引きあげて、この試料を化学分析して重量損耗を求め、銅板を100としてそれぞれ比較値で示した。また耐熱性は100×20×2mm(表面あらかし120)の試料を80-50Pb半田の浴槽中に2時間浸して引きあげたときに表面が半田で

完全にぬれている部分をはかり、銅板の試料のときのぬれ面積を100としてそれぞれ比較値で示した。

この表からわかるようにこの発明のものは、従来のものに比べて硬さと耐食性について著しい向上を示し、かつ耐熱性も同等であり、半田ごてとしては長寿命がはかられるものであつて、工業的にきわめて有用である。金属炭化物は特性の点、入手容易な点から実用的には炭化タングステン(WC)が適格であるが、炭化モリブデン(MoC)のほか炭化クロム(CrC)を用いてもこの発明の効果を示す。電気良導体金属としては、銅は熱容量が大で耐食性にすぐれ価格が安い点で好ましく、銀(Ag)はぬれ性の改善が著しい。添加金属としては、コバルト(Co)が炭化タングステンに対するバインダーとしての効果が大きく耐食性を向上させる点で好ましい。鉄(Fe)は最も安価に入ることができるものである。

前記は半田ごてのチップ部全体をこの発明の合金材料にて形成したものについて説明したが、これに限ることなく少なくともチップ部のろう材

と接触する部分がこの発明の材料にて成るものであればよい。また金属炭化物、電気良導体金属および添加金属の好ましい含有範囲はそれぞれ80-50wt%, 40-80wt%および0.1-10wt%である。上記の範囲をはずれるものはこの発明の目的とする半田ごての特性を得ることが困難である。


4. 図面の簡単な説明

図面は半田ごての正面図である。

1…半田ごて、2…チップ部。

(3257) 代理人 弁理士 井上 一 男

特開昭54-161509(3)



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.